



CEWELD SACW DUR 21

TYPE	Cobalt based fluxcored SAW wire for cladding against metal to metal wear, thermal schock and erosion.							
ANWENDUNGEN	Solving wear problems against chemicals, erosion, corosion, high temperatures, abrasion and combinations of those.							
EIGENSCHAFTEN	Excellent gliding properties against metal to metal wear due to low friction, Excellent against erosion and corrosion at high working temperatures upto 900°C. Crack free hard facing deposit against severe thermal shock and impact. To be used with fused flux CEWELD® FL 880.							
KLASSIFIKATION	EN ISO		14700: T Co1					
GEEIGNET FÜR	Cladding seats and valves in chemical industry, hot sharing blades, extrusion parts, coke hammers, turbine injectors, gas and steam turbine parts.							
ZULASSUNGEN								
SCHWEISSPOSITIONEN								
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Si	Mn	Cr	Ni	Mo	Fe	Co
	0.27	1.2	1	28	2.5	5	3.5	Rem.
MECHANISCHE GÜTEWERTE	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness		
	As Welded					30 HRc		
RÜCKTROCKNUNG	140°C / 24 hr							
GAS ACC. EN ISO 14175								



CEWELD SACW DUR 21

SACW DUR 21 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663417336