



CEWELD SS 6356 (40 HRc)

TYPE Cobalt alloyed age hardenable hardfacing alloy for Mig and Tig welding.

ANWENDUNGEN High alloyed, age-hardenable alloy for high wear resistant clad layers combined with galling and high working temperatures.

EIGENSCHAFTEN The weld deposit is, in the as-welded condition machinable, and the subsequent artificial aging optimises the resistance to hot wear and alternating temperatures.

KLASSIFIKATION EN ISO 14700: S Fe5

GEEIGNET FÜR Age-hardenable alloy for high wear resistant clad layers on cold and hot working tools. Repair, preventive maintenance and production of highly stressed cold and hot working tools, such as punching dies, cold and hot cutting knives, Al-dies cast moulds, cold forging dies, drawing, stamping- and chamfering tools.

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Ni	Co	Mo	Mn	Si	Fe
0.03	17	10	4	0.3	0.8	Rem.

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded	885	990		39 HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1, M13, M12