


CEWELD L-Ag5P

TYPE	Copper Phosphorus Silver Brazing Alloy.				
ANWENDUNGEN	Particularly recommended for sanitary and refrigerating equipment. Suitable for working temperatures up to 200 °C				
EIGENSCHAFTEN	Excellent flowing alloy with high purity offering strong brazing joints. Do not use in a sulphurous environment. Flux/Paste: CEWELD Super-Flux				
KLASSIFIKATION	AWS EN ISO F-nr	A 5.8: BCuP-3 17672: CuP 281 103			
GEEIGNET FÜR	Copper to Copper (without flux). Brass, Copper and Copper-Tin Alloys (with flux).				
ZULASSUNGEN					
SCHWEISSPOSITIONEN	      				
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	Cu Rem.	Ag 5	P 6		
MECHANISCHE GÜTEWERTE	Heat Treatment As Welded	R _{P0,2} (MPa)	R _m (MPa) 250	A5 (%) Hardness HRc	
RÜCKTROCKNUNG	Not required				
MELTING RANGE	645 - 815°C				
GAS ACC. EN ISO 14175					



CEWELD L-Ag5P

L-AG5P 1,5MM

Packaging	KG/unit	EanCode
D-300	10,11	8720663421487