



CEWELD SACW 350

TYPE Fluxcored SAW wire for cladding and rebuilding wornout parts.

ANWENDUNGEN 325-375 HB, Hardfacing and rebuilding alloy for wornout wheels, rails, tracks, tires, conveyors, crossings, buffer layers prior to Hardfacing. Excellent wear and abrasion resistance against heavy impact and shock, good machinable with carbide tools

EIGENSCHAFTEN To be used with neutral flux and basicity above 1.5. Suitable fluxes are FL 851 and FL 155

KLASSIFIKATION EN ISO 14700: T Fe2

GEEIGNET FÜR Rails repair, crossings, concrete bars, crane, railway and tram tracks, conveyors and transport surfaces, tires, bucket and loader teeth, crusher jaws, buffer layers etc.

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Cr
0.12	0.8	1.8	1

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded				350 HB

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175