



CEWELD SA 317L

TYPE	Stainless steel SAW welding wire with excelent corosion properties against acid chloride containing environments.									
ANWENDUNGEN	For SAW welding stabilized and un-stabilized CrNiMo(N) type of steels with high corrosion resistance. Also suitable for dissimilar welds between steel and stainless steel or dissimilar stainless steels. 317L has good resistance to general corrosion and pitting due to its high content of molybdenum. The alloy is used in severe corrosion conditions such as in the petrochemical, pulp, cotton and paper industries.									
EIGENSCHAFTEN	Austenitic, non magnetic stainless steel alloy with high mechanical properties and excellent weldability, corrosion resistance is better than AISI 316 due to the high Mo. content and also offers excellent corrosion resistance against delude hot acids. Suitable for use up to 400°C. SA 317L is best to be used in combination with FL 838									
KLASSIFIKATION	AWS EN ISO W.Nr. F-nr FM		6							
GEEIGNET FÜR	Designed for joining corrosion resistant CrNiMoN steel as well as for austenitic-ferritic joints. ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 26, 27, 28 1.4429, 1.4434, 1.4435, 1.4436, 1.4438, 1.4439, 1.4453, 1.4583, X2CrNiMoN 17 13 5, X2CrNiMoN 17 13 3, X2CrNiMo 18 15 4, X10CrNiMoNb 18 12, X2CrNiMoN17-13- 3, X2CrNiMoN18-12-4, X2CrNiMo18-14-3, X3CrNiMnMoN19-16 UNS S31600, S31653, S31703, S31726, S31753 AISI 316Cb, 316L, 316LN, 317L, 317LN, 317LMN									
ZULASSUNGEN	CE									
SCHWEISSPOSITIONEN										
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	С	Si	Mn		Ρ	S	Cr	Ni	Мо	
	0.02	0.55	2	0.	02	0.01	19.5	14	3.5	
MECHANISCHE GÜTEWERTE	Heat		Rm	A5	Impact Energy (J) ISO-V					
	Treatme	nt (MP		(%)	RT				Hardness	
	As Welde	ed 39	0 530	33	70				HRc	
RÜCKTROCKNUNG	Not required									

GAS ACC. EN ISO 14175





CEWELD SA 317L

SA 317L 2,4MM	Packaging	KG/unit	EanCode		
	K-415	25	8720663415288		
SA 317L 3,2MM	Packaging	KG/unit	EanCode		
	K-415	25	8720663415318		