

# CEWELD CuNi30Fe Tig

**TYPE** Copper-Nickel alloyed Tig filler metal.

**ANWENDUNGEN** This Copper-Nickel weld metal is widely used for marine and desalination applications. Dissimilar welding applications for this alloy are joints between Monel alloys or Nickel 200 and Copper-Nickel alloys. Often used for surfacing on steel by using Ceweld NiTi-3 as a barrier layer. Shipbuilding, seawater evaporation plants, tubes, pump building, offshore, desalting equipment and parts etc.

**EIGENSCHAFTEN** Sound, pore free deposits on ferrous and non-ferrous base materials offering excellent resistance to corrosion in sea water.

**KLASSIFIKATION**  
 AWS A 5.7: ERCuNi  
 EN ISO 24373: Cu 7158 / CuNi30Mn1FeTi  
 W.Nr. 2.0837  
 F-nr 34

**GEEIGNET FÜR** (Monel 67): Wrought and cast alloys of 70-30, 80-20 and 90-10 copper nickel alloys, Monel 450, (alloy 450), Nickel 200, CuNi10Fe, CuNi20Fe (2.0878), CuNi30Fe (2.0882), 2.0872 - CuNi 10 Fe 1 Mn (CuNi 10 Fe),

**ZULASSUNGEN**

**SCHWEISSPOSITIONEN**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**


Si	Mn	P	Ti	Fe	Pb	Cu+Ag	Ni+Co	S
0.2	0.5	0.01	0.4	0.6	0.01	Rem.	31	0.01

**MECHANISCHE GÜTEWERTE**

Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness
				RT		
As Welded	200	420	36	200		115 HB

**RÜCKTROCKNUNG** Not required

**GAS ACC. EN ISO 14175** I1, I3



# CEWELD CuNi30Fe Tig

CUNI30FE TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409584
CUNI30FE TIG 1,6 X 914MM	Packaging	KG/unit	EanCode
	Tube	4,54	8720663409591
CUNI30FE TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409607
CUNI30FE TIG 2,0 X 914MM	Packaging	KG/unit	EanCode
	Tube	4,54	8720663409614
CUNI30FE TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409621
CUNI30FE TIG 2,4 X 914MM	Packaging	KG/unit	EanCode
	Tube	4,54	8720663409645
CUNI30FE TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409652
CUNI30FE TIG 3,2 X 914MM	Packaging	KG/unit	EanCode
	Tube	4,54	8720663409669