




CEWELD SG Ni2,5 Tig

TYPE	Solid welding wire for extra low temperature applications.							
ANWENDUNGEN	Filler metal developed for fine grain steels and cold-tough steels. Typical applications are welding boilers for liquid petrol gas (LPG)							
EIGENSCHAFTEN	A copper coated, Ni-alloyed (2,4% Ni), solid wire for low temperature steels in applications such as vessels, pipes and in the offshore industry with a minimum yield strength of 470 MPa. The wire provides excellent impact toughness down to -60°C.							
KLASSIFIKATION	AWS	A 5.28: ER 80S-Ni2						
	EN ISO	636-A: W 42 9 2Ni2						
	F-nr	6						
	FM	1						
GEEIGNET FÜR	For cryogenic construction steels and Ni bearing low temperature steels.							
	11MnNi5-3, 13MnNi6-3, 15NiMn6, S275NL-S460NL, S275ML-S460ML, P275NL2-P460NL2, P355ML2-P460ML2							
	ASTM: A203 grade A/B, A333/A334 grades 1/6/7, A350 grade LF2/LF5/LF6, A352 grade LC1/LC2							
ZULASSUNGEN	CE							
SCHWEISSPOSITIONEN								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Ni				
	0.1	0.5	1.05	2.45				
MECHANISCHE GÜTEWERTE	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness
	As Welded	540	630	28	-40°C	-60°C	-80°C	HRc
					100	60	47	
RÜCKTROCKNUNG	Not required							
GAS ACC. EN ISO 14175	I1							



CEWELD SG Ni2,5 Tig

SG NI2,5 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663405784
SG NI2,5 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663405791
SG NI2,5 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663405807
SG NI2,5 TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663405814