



# CEWELD AA NiCrO 625B

TYPE	Basic flux-cored nickel base welding wire for gas shielded arc welding.																		
ANWENDUNGEN	AA Nicro 625B is developed for welding and cladding nickel-based alloys such as alloy 625 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels or to stainless steels and for joining 6% molybdenum super austenitic steels.																		
EIGENSCHAFTEN	Latest generation basic slag guarantees optimum metallurgical quality and attractive welder appeal. The weld deposit meets the NiCrMo-3 requirements. Better bead aspect and shape compare to solid wires with better arc stability and improved wetting properties with less spatters.																		
KLASSIFIKATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.34: E NiCrMo3T1-4</td> </tr> <tr> <td>EN ISO</td> <td>12153-A: T Ni 6625 (NiCr22Mo9Nb) B M21 3</td> </tr> <tr> <td>F-nr</td> <td>43</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> </table>	AWS	A 5.34: E NiCrMo3T1-4	EN ISO	12153-A: T Ni 6625 (NiCr22Mo9Nb) B M21 3	F-nr	43	FM	6										
AWS	A 5.34: E NiCrMo3T1-4																		
EN ISO	12153-A: T Ni 6625 (NiCr22Mo9Nb) B M21 3																		
F-nr	43																		
FM	6																		
GEEIGNET FÜR	<p><b>Ni 6625 / NiCr22Mo9Nb / 2.4831</b>            1.4547 - 1.4876 - 1.4958 - 2.4816 - 2.4856 - 2.4858 - 1.5656 - 1.4529 - 1.4539 - 2.4660            X1CrNiMoCuN20-18-7 - X10NiCrAlTi32-20 - X5NiCrAlTi31-20 - NiCr15Fe - NiCr22Mo9Nb - NiCr21Mo            - X1NiCrMoCuN25 20 6 - X1NiCrMoCuN25 20 5 - NiCr21Mo - 8XNi9            UNS: S31254 - N08800 - N08810 - N06600 - N06625 - N08825 - N08926 - N08020            ASTM A 553 Gr.1, Alloy 600, Alloy 600 L, Alloy 625, Alloy 800 / 800H, Alloy 825            Alloy 254 SM - Sanicro 28</p>																		
ZULASSUNGEN																			
SCHWEISSPOSITIONEN																			
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Nb</th> <th>Fe</th> <th>S</th> </tr> </thead> <tbody> <tr> <td>0.03</td> <td>0.35</td> <td>0.45</td> <td>21.5</td> <td>60.5</td> <td>9.5</td> <td>3.4</td> <td>4</td> <td>0.01</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	Nb	Fe	S	0.03	0.35	0.45	21.5	60.5	9.5	3.4	4	0.01
C	Si	Mn	Cr	Ni	Mo	Nb	Fe	S											
0.03	0.35	0.45	21.5	60.5	9.5	3.4	4	0.01											
MECHANISCHE GÜTEWERTE	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>p0,2</sub> (MPa)</th> <th rowspan="2">R<sub>m</sub> (MPa)</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">-196°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>500</td> <td>780</td> <td>40</td> <td colspan="2">60</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness	-196°C		As Welded	500	780	40	60		HRc		
Heat Treatment	R <sub>p0,2</sub> (MPa)					R <sub>m</sub> (MPa)	A <sub>5</sub> (%)		Impact Energy (J) ISO-V		Hardness								
		-196°C																	
As Welded	500	780	40	60		HRc													
RÜCKTROCKNUNG	140°C / 24 hr																		
GAS ACC. EN ISO 14175	M21																		