

# CEWELD Powder DUR 6 Mo (Alloy F75)

TYPE	Gas atomized spherical Cobalt-Chromium-Molybdenum alloy.								
ANWENDUNGEN	PTA and or laser overlay welding on wear parts that need to outlast new parts where high temperatures combined with corrosion and wear resistance is required. 3D printing of parts for medical applications as prostatic implants such as replacement hips and knee condyles.								
EIGENSCHAFTEN	CoCrMo alloys are non magnetic and offers extreem resistance against fatigue. The alloy offers excelent polishing characteristics and ensures long tool life.								
KLASSIFIKATION	EN ISO 14232-1 Co-Cr-Mo 63/28/6								
GEEIGNET FÜR	Replacement hips, knee parts, condyles, Gas turbine parts, fuel nozzles, orthopedic implants.								
ZULASSUNGEN									
SCHWEISSPOSITIONEN									
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table><thead><tr><th>Co</th><th>Cr</th><th>Mo</th><th>Other</th></tr></thead><tbody><tr><td>Rem.</td><td>27</td><td>6</td><td>2.6</td></tr></tbody></table>	Co	Cr	Mo	Other	Rem.	27	6	2.6
Co	Cr	Mo	Other						
Rem.	27	6	2.6						
MECHANISCHE GÜTEWERTE									
RÜCKTROCKNUNG	Not required								
GAS ACC. EN ISO 14175									