



CEWELD CuSn

TYPE Copper welding wire alloyed with Sn for Mig and Tig welding

ANWENDUNGEN Boilers and tubes out of copper or copper alloys, oven soldering etc..

EIGENSCHAFTEN

- High quality alloyed copper wire
- Sound, pore free deposits and good electrical conductivity
- Excellent corrosion resistance

KLASSIFIKATION

AWS	A 5.7: ERCu
EN ISO	24373: Cu 1898 / CuSn1
W.Nr.	~2.1006
F-nr	31

GEEIGNET FÜR Bronze alloy with minimally 0.8 tin for virtually all welding procedures. Very good deoxidisation. Surfacing and joining of Cu and copper- alloys. Widely used in oven soldering.
 2.0040 - OF-Cu,
 2.0070 - SE-Cu,
 2.0076 - SW-Cu,
 2.0090 - SF-Cu

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

Si	Mn	Cu	Sn
0.3	0.3	98.5	0.8

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		220		60 HB

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD CuSn

CUSN 0,8MM	Packaging	KG/unit	EanCode
	D-300	15	8720663408624

CUSN 1,0MM	Packaging	KG/unit	EanCode
	BS-300	15	8720663408631

CUSN 1,2MM	Packaging	KG/unit	EanCode
	BS-300	15	8720663408648
	Drum	250	8720682051528

CUSN 1,6MM	Packaging	KG/unit	EanCode
	BS-300	15	8720663408655