



CEWELD OA 410 NiMo

TYPE Self-Shielded fluxcored CrNiMo wire

APPLICATIONS Bridge bearings, sealing surfaces, corrosion, slide ring sealing, centrifuge, continuous casting rolls

PROPERTIES The corrosion resistant deposit with a medium hardness is resistant against impact wear as well as permanent stress by heat influence, metal wear and high surface pressure

CLASSIFICATION

AWS	A 5.22: E410NiMoT0-3
EN ISO	14700: T Fe7
W.Nr.	1.4351

SUITABLE FOR **13%Cr - 4%Ni - 0,5%Mo Steel**
 1.4000, 1.4001, 1.4002, 1.4313, 1.4317, 1.4407, 1.4413, 1.4414,
 GX4CrNi13-4, X3CrNiMo13-4, GX5CrNiMo13-4, GX4CrNiMo13-4, X 6 Cr 13, X 7 Cr 14, X 6 CrAl 13
 ACI Gr. CA 6 NM

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


C	Si	Mn	P	Cr	Ni	Mo	Fe
0.05	0.9	1	0.025	14	4.5	0.75	Rem.

MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded				40 HRc

REDRYING 140°C / 24 hr

GAS ACC. EN ISO 14175



CEWELD OA 410 NiMo

OA 410 NIMO 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663411808