

CEWELD AA MnCr



ТҮРЕ	Gas shielded fluxcored welding wire for rebuilding and buffer layers before hardfacing with extreme resistance to heavy impact loads.								
APPLICATIONS	Rebuilding heavy steel parts, buffer layers, winches, rails, rails crossings, dredger teeth, blast furnace mantles etc								
PROPERTIES	Austenitic deposit with strain hardening properties and no limmits in the number of layers. The deposit is non magnetic and can not be flame cut and is extreme resistant to heavy impact loads								
CLASSIFICATION	EN ISO			14700: T Fe9					
SUITABLE FOR	Rebuilding wornout parts, buffer layers, rebuilding rails and or crossings, dredger teeth, blast furnace mantles, winches.								
APPROVALS									
WELDING POSITIONS									
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	с	Si	Mn	Cr	Ni	Мо	v	Fe	
	0.4	0.4	16	14	1.2	0.6	0.2	Rem.	
MECHANICAL PROPERTIES	Heat Treatment			P0,2 Pa)	Rm (MPa)	A5 (%)	Hardness		
	As Welded						240 HB		
REDRYING	Not required								
GAS ACC. EN ISO 14175	None, M21								





CEWELD AA MnCr

AA MNCR 1,2MM	Packaging	KG/unit	EanCode		
	BS-300	15	8720663402943		
AA MNCR 1,6MM					
AA MINCI 1,0MM	Packaging	KG/unit	EanCode		
	BS-300	15	8720663402950		