

CEWELD FL CS155

TYPE	Fused flux with very low hydrogen content for SAW welding.
APPLICATIONS	Boiler works, pipes, ship building, structural steel works, tanks and pressure vessels, offshore applications etc..
PROPERTIES	FL CS155 is a fused flux for SAW welding un and low alloyed carbon steels. Basicity: about 1,05 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 1-16
CLASSIFICATION	EN ISO 14174: SF CS 1 56 AC H5
SUITABLE FOR	Unalloyed steels: St 33 – St 52, Ship building: A, E, AH, EH , Boiler steels: HI-HIII, 17Mn4, 19Mn5, Pipe steels: St 37.0/4 – St 52.0/4, Fine-grain steels:StE 255 – StE 420, X70

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)

	CaO+MgO+SiO ₂	CaO+MgO
	55	15

MECHANICAL PROPERTIES

REDRYING Not required

GAS ACC. EN ISO 14175

CEWELD FL CS155

FL CS155 0,1 - 1,6MM

Packaging	KG/unit	EanCode
Bag	25	8720663404022