



CEWELD SA 347

TYPE Solid stainless steel welding wire for submerged arc welding 18Cr/10Ni alloys stabilized with Ti of Nb

APPLICATIONS Solid stainless steel wire for SAW welding Niobium or Titanium stabilized stainless steels.

PROPRIÉTÉS This wire can be used for stainless steels stabilized with Ti of Nb like grades 321 and 347. But also for unstabilized alloys like 304 or 304L. High resistance against intergranular corrosion. Fused flux FL 880 of agglomerated flux FL 838 can be used

CLASSIFICATION

AWS	A 5.9: ER347
EN ISO	14343-A: S 19 9 Nb
W.Nr.	1.4551
F-nr	6
FM	5

CONVIENT POUR 1.4541, 1.4550, 1.4552 1.4319, 1.4306, 1.4306, 1.4301, 1.4303, 1.4308, 1.4310, 1.4312, 1.4878 X 6 NiTi 18 10, X 6CrNiNb 18 10, G-X 5CrNiNb 18 9, X 5CrNi 18 7, X 2CrNi 19 11, G-X 2CrNi 18 9, X 5CrNi 18 10, X 5CrNi 18 12 G-X, 6CrNi 18 9, X 12CrNi 17 7, G-X 10CrNi 18 8
AISI: 321, 347

AGRÉMENTS CE

POSITIONS DE SOUDAGE



**ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL
D'APPORT (%)**

C	Si	Mn	P	S	Cr	Ni	Nb
0.06	0.5	2	0.02	0.02	20	10	0.1

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT	-196°C	
As Welded	380	600	35	80	40	HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175