





# CEWELD AlSi 5

TYPE	Mig aluminium welding wire alloyed with silicon														
APPLICATIONS	He is a MIG filler metal for welding Aluminium alloys with maximum 2% alloying elements and for Aluminium alloys containing up to 7% Si.(after anodizing welding will be of a dark grey colour)														
PROPRIÉTÉS	Thanks to its excellent weldability and good penetration this alloy is used mainly in construction and automotive industry. The silicon addition results in improved fluidity (wetting action), making the alloy the preferred choice of welders. The alloy is not sensitive to weld cracking and produces bright, almost smut-free welds. Not recommended for anodizing. Non-heat treatable. Thicker sections should be preheated (150°C) prior to welding.														
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.10: ER4043</td> </tr> <tr> <td>EN ISO</td> <td>18273: S Al 4043A (AlSi5(A))</td> </tr> <tr> <td>W.Nr.</td> <td>3.2245</td> </tr> <tr> <td>F-nr</td> <td>23</td> </tr> </table>	AWS	A 5.10: ER4043	EN ISO	18273: S Al 4043A (AlSi5(A))	W.Nr.	3.2245	F-nr	23						
AWS	A 5.10: ER4043														
EN ISO	18273: S Al 4043A (AlSi5(A))														
W.Nr.	3.2245														
F-nr	23														
CONVIENT POUR	AlMgSi 0, AlSiMg (A), AlSi 1 MgMn, AlMg1SiCu, AlCuMg 1, AlMgSi 1, AlZn 4,5 Mg 1 3.1325, 3.3206, 3.3210, 3.2315, 3.3211, 3.4335 EN AW 6060, EN AW 6005A, EN AW 6082, EN AW 6061, EN AC 45000,														
AGRÉMENTS	CE														
POSITIONS DE SOUDAGE															
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>Si</th> <th>Mn</th> <th>Ti</th> <th>Fe</th> <th>Cu</th> <th>Al</th> <th>Mg</th> </tr> </thead> <tbody> <tr> <td>5</td> <td>0.1</td> <td>0.1</td> <td>0.3</td> <td>0.1</td> <td>Rem.</td> <td>0.1</td> </tr> </tbody> </table>	Si	Mn	Ti	Fe	Cu	Al	Mg	5	0.1	0.1	0.3	0.1	Rem.	0.1
Si	Mn	Ti	Fe	Cu	Al	Mg									
5	0.1	0.1	0.3	0.1	Rem.	0.1									
PROPRIÉTÉS MÉCANIQUES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>Heat Treatment</th> <th>R<sub>P0.2</sub> (MPa)</th> <th>R<sub>m</sub> (MPa)</th> <th>A5 (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>100</td> <td>160</td> <td>17</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Hardness	As Welded	100	160	17	HRc				
Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Hardness											
As Welded	100	160	17	HRc											
ETUVAGE	Not required														
GAS ACC. EN ISO 14175	I1, I3														



# CEWELD ALSi 5

ALSI 5 0,8MM	Packaging	KG/unit	EanCode
	D-100	0,5	8720663407474
	D-200	2	8720663407467
	D-300	7	8720663407450

ALSI 5 0,9MM	Packaging	KG/unit	EanCode
	D-300	7	8720663407504

ALSI 5 1,0MM	Packaging	KG/unit	EanCode
	D-100	0,5	8720663407481
	D-200	2	8720663407498
	D-300	7	8720663407511
	Drum	80	8720663407528

ALSI 5 1,2MM	Packaging	KG/unit	EanCode
	D-100	0,5	8720663407559
	D-200	2	8720663407566
	D-300	7	8720663407535
	Drum	80	8720663407542

ALSI 5 1,6MM	Packaging	KG/unit	EanCode
	BS-300	7	8720663407573

ALSI 5 2,0MM	Packaging	KG/unit	EanCode
	D-300	7	8720663407580