



# CEWELD ER 120 S-1 Tig

**TYPE** Extreme high tensile strength alloy with excellent impact properties for fine grain steels exceeding 890 MPa yield strength.

**APPLICATIONS** Welding materials such as S960QL – S1100Q and other similar fine grain cold tough steels. Offshore, crane building etc.

**PROPRIÉTÉS** Extreme high tensile strength alloy with very good mechanical properties and perfect welding characteristics. High impact strength at very low temperatures with exceptional plasticity of the weld deposit. Weldable with Co2 and Mix gas.

**CLASSIFICATION**

AWS	A 5.28: ER 120S-G
EN ISO	16834-A: W 89 5 I1 Mn4Ni2CrMo
F-nr	6
FM	2

**CONVIENT POUR** **Reh ≤ 960 MPa ISO 15608: ~3.1, 3.2 (Reh > 690 MPa)**  
 1.8796, 1.8925, 1.8940, 1.8983, 1.8797, 1.8933, 1.8934, 1.8941, 1.8997  
 S690Q-S890Q, S690QL-S890QL, S960Q, S960QL, S720MC  
 ASTM A 709 Gr. 100 Type B, E, F, H, Q, HPS 100W  
 N-A-XTRA M 700, PAS 700, alform 700 M, alform 900 x-treme, alform® 960 x-treme, Strenx 700-960, DILLIMAX 700-960

**AGRÉMENTS** CE

**POSITIONS DE SOUDAGE**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**

C	Si	Mn	Cr	Ni	Mo
0.08	0.6	1.8	0.3	2.25	0.55

**PROPRIÉTÉS MÉCANIQUES**

Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V	Hardness
				-60°C	
As Welded	980	1090	18	50	HRc

**ETUVAGE** Not required

**GAS ACC. EN ISO 14175** I1



# CEWELD ER 120 S-1 Tig

ER 120 S-1 TIG 1,6 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417237

ER 120 S-1 TIG 2,0 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417244

ER 120 S-1 TIG 2,4 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417268

ER 120 S-1 TIG 3,2 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417275