



CEWELD OA 58-66B

TYPE	High alloyed seamless metal cored wire for hardfacing against extreme abrasion.		
APPLICATIONS	Rebuilding wornout parts or protecting new machine parts to increase life that suffer from extreme abrasive wear		
PROPRIÉTÉS	High C-, Cr-, B-alloyed flux-cored wire electrode which forms extremely hard carbides for extremely hard deposits on parts subject to excessively heavy abrasive wear weldable with and without protective gas. Verry good wear resistance due to excellent first layer hardness properties. More than 1 or 2 layers should not be deposited. A Buffer layer with CEWELD® OA 4370 or CEWELD® OA MnCr is recommended in case of old layers or critical base metals. Weldable with M21 or without shielding gas.		
CLASSIFICATION	EN ISO	14700: T ZFe14	
CONVIENT POUR	58-66 HRC Hardfacing alloy used in mining, agriculture and steel mills, conveyor chains, agriculture, construction, mixer blades, paddles, cement pumps with excelent abrasion and wear resistance against sand and minerals		

AGRÉMENTS

POSITIONS DE SOUDAGE



ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)

C	Si	Mn	Cr	B
2.6	0.6	0.9	17	0.9

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				62 HRc

ETUVAGE 140°C / 24 hr

GAS ACC. EN ISO 14175