

# CEWELD P24 Tig

TYPE	Tig welding wire for creep resistant P/T 24 type of steels.	
APPLICATIONS	The alloy finds use for waterwalls in ultra-super-critical (USC) boilers in the power generating industry.	
PROPRIÉTÉS	TIG/GTAW rod for T24 creep resistant steel. The T24 alloy is a modified 2.25%Cr1%Mo alloy with additions of Nb and V to improve high temperature creep performance. Interpass temperature: max. 300°C	
CLASSIFICATION	AWS	A 5.28: R90S-B24
	EN ISO	21952-A: W ZCrMo2VNb
	W.Nr.	~1.7378
	F-nr	6
	FM	3

CONVIENT POUR alloy 24, 2.5%Cr1%Mo modified, creep resisting ferritic steels. X7CrMoVTiB 10-10 1.7378 / 7CrWVMoNb9-6 - 1.8201  
 ASTM: A/SA 335 Grade P24 - A/SA 213 Grade T24 A/SA 335 Grade P23 - A/SA 213 Grade T23

AGRÉMENTS CE



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Mo	V	Nb
	0.1	0.25	0.9	0.01	0.01	2.3	1	0.3	0.02

PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness
					RT		
	730°C- 760°C 1h	650	750	20	50		HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175 I1