

# CEWELD 309H Tig

**TYPE** Solid stainless steel rod with high carbon content for high temperature applications. (Type 309H, 22 12, 1.4829

**TOEPASSINGEN** CEWELD 309H Tig is scale resistant up to 1050° C. Buffer layers before hard facing, cladding and joining of similar austenitic steels, specially recommended for use in oxidizing gasses with nitrogen and gasses containing small amounts of oxygen.

**EIGENSCHAPPEN** CEWELD 309H Tig have high mechanical properties and very good weldability, suitable for high operating temperatures up to 1100°C.

**CLASSIFICATIE**

AWS	A 5.9: ER309
EN ISO	14343-A: W 22 12 H
W.Nr.	1.4829
F-nr	6
FM	5

**GESCHIKT VOOR** **ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21, 23% Cr, 12%Ni Type**  
 1.2780, 1.4541, 1.4550, 1.4710, 1.4712, 1.4713, 1.4724, 1.4729, 1. 4740, 1.4741, 1.4742, 1.4746, 1.4762, 1.4745, 1.4825, 1.4826, 1.4828, 1.4832, 1.4878,  
 X15CrNiSi20 12, G-X 40 CrNiSi20 9, G-X 30 CrSi 6, G-X 40 CrSi 13, G-X 40 CrSi 17, G-X 25 CrNiSi 18 9, X 15 CrNiSi 20 12, X 12 CrNiTi 18 9  
 AISI 446, 442, 309,  
 UNS S30900, S44200, S4460

**GOEDKEURINGEN** CE

**LASPOSITIES**



**TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)**

C	Si	Mn	Cr	Ni
0.09	0.6	1.3	23	13

**MECHANISCHE WAARDEN**

Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	380	630	30	70	HRc

**HERDROGEN** Not required

**GAS ACC. EN ISO 14175** I1