

# CEWELD Alloy 230 Tig

TYPE	Nickel based Tig filler metal for welding similar NiCrW alloys.																		
TOEPASSINGEN	In the chemical process industry, CEWELD® Alloy 230 is used for catalyst grid supports in ammonia burners, high-strength thermocouple protection tubes, high-temperature heat exchangers, ducts, high-temperature bellows, and various other key process internals. In the industrial heating industry, applications for 230 alloy include furnace retorts, chains and fixtures, burner flame shrouds, recuperator internals, dampers, nitriding furnace internals, heat-treating baskets, grates, trays, sparger tubes, thermocouple protection tubes, cyclone internals, and many more.																		
EIGENSCHAPPEN	CEWELD® Alloy 230 combines properties which make it ideally suited for a wide variety of component applications in the aerospace and power industries. It is used for combustion cans, transition ducts, flame holders, thermocouple sheaths, and other important gas turbine components.																		
CLASSIFICATIE	AWS A 5.14: ERNiCrWMo-1 EN ISO 18274: S Ni 6231(NiCr22W14Mo2) W.Nr. 2.4733 F-nr 43 FM 6																		
GESCHIKT VOOR	Haynes Alloy 230, UNS N06617, AMS 5839																		
GOEDKEURINGEN																			
LASPOSITIONS	 PA  PB  PC  PD  PE  PF  PG																		
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th><th>Si</th><th>Mn</th><th>Cr</th><th>Ni</th><th>Mo</th><th>W</th><th>Co</th><th>Al</th></tr> </thead> <tbody> <tr> <td>0.1</td><td>0.4</td><td>0.5</td><td>22</td><td>57</td><td>2</td><td>14</td><td>4</td><td>0.3</td></tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	W	Co	Al	0.1	0.4	0.5	22	57	2	14	4	0.3
C	Si	Mn	Cr	Ni	Mo	W	Co	Al											
0.1	0.4	0.5	22	57	2	14	4	0.3											
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th>Heat Treatment</th><th>R<sub>P0,2</sub> (MPa)</th><th>Rm (MPa)</th><th>A5 (%)</th><th>Hardness</th></tr> </thead> <tbody> <tr> <td>As Welded</td><td>490</td><td>785</td><td>48</td><td>HRc</td></tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	Rm (MPa)	A5 (%)	Hardness	As Welded	490	785	48	HRc								
Heat Treatment	R <sub>P0,2</sub> (MPa)	Rm (MPa)	A5 (%)	Hardness															
As Welded	490	785	48	HRc															
HERDROGEN	Not required																		
CURRENT TYPE:	DC-																		
GAS ACC. EN ISO 14175	I1																		



# CEWELD Alloy 230 Tig

ALLOY 230 TIG 1,6 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720682051399

ALLOY 230 TIG 2,0 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663424235

ALLOY 230 TIG 2,4 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663420152