



CEWELD SG Ni2,5

| TYPE | Massief verkoperde lasdraad voor het lassen van fijnkorrelige en koudebestendige staalsoorten | | | | | | | | | | | | | | | | | | | |
|--|---|----------------|-------------------------|----------------------|--------------------------|-------------------------|--------------------|-------------------------|----------|-------|----------|-------|-----------|-----|-----|----|-----|----|----|-----|
| TOEPASSINGEN | Dit toevoegmetaal is ontwikkeld voor fijnkorrelig staal en koudebestendig staal. Typische toepassingen zijn het lassen van ketels voor vloeibaar petroleumgas (LPG) | | | | | | | | | | | | | | | | | | | |
| EIGENSCHAPPEN | Massief verkoperde Ni-gelegeerde (2,4% Ni) lasdraad voor laagtemperatuurstaal in toepassingen zoals schepen, buizen en in de offshore-industrie met een minimale vloeigrens van 470 Mpa. De draad heeft een uitstekende slagvastheid tot -60°C. | | | | | | | | | | | | | | | | | | | |
| CLASSIFICATIE | <table border="0"> <tr> <td>AWS</td> <td>A 5.28: ER 80S-Ni2</td> </tr> <tr> <td>EN ISO</td> <td>14341-A: G 46 6 M21 2Ni2</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>1</td> </tr> </table> | AWS | A 5.28: ER 80S-Ni2 | EN ISO | 14341-A: G 46 6 M21 2Ni2 | F-nr | 6 | FM | 1 | | | | | | | | | | | |
| AWS | A 5.28: ER 80S-Ni2 | | | | | | | | | | | | | | | | | | | |
| EN ISO | 14341-A: G 46 6 M21 2Ni2 | | | | | | | | | | | | | | | | | | | |
| F-nr | 6 | | | | | | | | | | | | | | | | | | | |
| FM | 1 | | | | | | | | | | | | | | | | | | | |
| GESCHIKT VOOR | <p>For cryogenic construction steels and Ni bearing low temperature steels.</p> <p>11MnNi5-3, 13MnNi6-3, 15NiMn6, S275NL-S460NL, S275ML-S460ML, P275NL2-P460NL2, P355ML2-P460ML2</p> <p>ASTM: A203 grade A/B, A333/A334 grades 1/6/7, A350 grade LF2/LF5/LF6, A352 grade LC1/LC2</p> | | | | | | | | | | | | | | | | | | | |
| GOEDKEURINGEN | CE | | | | | | | | | | | | | | | | | | | |
| LASPOSITIES | | | | | | | | | | | | | | | | | | | | |
| TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%) | <table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Ni</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.5</td> <td>1.1</td> <td>0.015</td> <td>0.015</td> <td>2.5</td> </tr> </tbody> </table> | C | Si | Mn | P | S | Ni | 0.1 | 0.5 | 1.1 | 0.015 | 0.015 | 2.5 | | | | | | | |
| C | Si | Mn | P | S | Ni | | | | | | | | | | | | | | | |
| 0.1 | 0.5 | 1.1 | 0.015 | 0.015 | 2.5 | | | | | | | | | | | | | | | |
| MECHANISCHE WAARDEN | <table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{p0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="3">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>-40°C</th> <th>-60°C</th> <th>-70°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>540</td> <td>630</td> <td>28</td> <td>100</td> <td>60</td> <td>47</td> <td>HRc</td> </tr> </tbody> </table> | Heat Treatment | R _{p0,2} (MPa) | R _m (MPa) | A ₅ (%) | Impact Energy (J) ISO-V | | | Hardness | -40°C | -60°C | -70°C | As Welded | 540 | 630 | 28 | 100 | 60 | 47 | HRc |
| Heat Treatment | R _{p0,2} (MPa) | | | | | R _m (MPa) | A ₅ (%) | Impact Energy (J) ISO-V | | | Hardness | | | | | | | | | |
| | | -40°C | -60°C | -70°C | | | | | | | | | | | | | | | | |
| As Welded | 540 | 630 | 28 | 100 | 60 | 47 | HRc | | | | | | | | | | | | | |
| HERDROGEN | Not required | | | | | | | | | | | | | | | | | | | |
| GAS ACC. EN ISO 14175 | M21 | | | | | | | | | | | | | | | | | | | |



CEWELD SG Ni2,5

SG NI2,5 0,8MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663405746 |

SG NI2,5 1,0MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663405753 |

SG NI2,5 1,2MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663405760 |

SG NI2,5 1,6MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663405777 |