



CEWELD AA CuAl12NiFe

TYPE	Copper-Aluminum FCAW composite welding wire for cladding applications.	
TOEPASSINGEN	Cladding components undergoing metal to metal wear with high friction and or heavy surface loads on top of cast iron, steels and or bronzes.	
EIGENSCHAPPEN	<ul style="list-style-type: none"> Special alloyed copper composite wire suitable for the Mig process The weld metal is a Cu-Al-Ni bronze with extreme high aluminium content. Sound, pore free deposits with excellent sliding properties and low friction. 	
CLASSIFICATIE	EN ISO	14700: T Cu1
GESCHIKT VOOR	Cu – Mn – Ni – Al bronze	

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

Mn	Ni	Fe	Cu	Al
0.9	4.5	2.2	Rem.	12

MECHANISCHE WAARDEN

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				320 HB

HERDROGEN Not required

GAS ACC. EN ISO 14175 11, 13



CEWELD AA CuAl12NiFe

AA CUAL12NIFE 1,2MM

Packaging	KG/unit	EanCode
D-300	13	8720663408938

AA CUAL12NIFE 1,6MM

Packaging	KG/unit	EanCode
D-300	13	8720663408952