



CEWELD AA CrCoMo 46

- TYPE** High-alloyed tubular wire on a Cr-Co-Mo basis for high temperature applications.
- TOEPASSINGEN** The characteristics of the deposit are comparable with cobalt-base alloys in terms of thermal shock and corrosion resistance that makes this alloy applicable for overlaying parts that are subject to high temperatures combined with corrosion attack, wear and thermal shock combinations. AA CrCoMo 46 can be used as intermediate layer against metal to metal wear at high pressure loads.
- EIGENSCHAPPEN** Very good corrosion resistance combined with excellent hardness properties at temperatures up to 650°C. Scale resistant till 900°C and excellent strength at high working temperatures. Excellent weldability and often used as economical alternative for „stellite“
- CLASSIFICATIE** EN ISO 14700: T Fe3
- GESCHIKT VOOR** Hot rolling parts for continuous casting, hotpress tools, pump parts, sleeves, mandrels, forging hammers, chemical and glass industry.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				47 HRc

HERDROGEN 140°C / 24 hr

GAS ACC. EN ISO 14175 M21