



CEWELD 21-33Mn

TYPE	Filler metal for heat resistant stainless steel with simmilar nature and composition
TOEPASSINGEN	Joining and cladding high heat resistant CrNi-steels of the same kind and Cast steels in a low sulphurous environment.
EIGENSCHAPPEN	Recommended for operating temperatures up to 1050°C in carburized invironments in ovens in petrochemical plants.
CLASSIFICATIE	EN ISO 14343-A: G Z 21 33 Mn Nb W.Nr. 1.4850 (mod)
GESCHIKT VOOR	1.4876, 1.4859, 1.4958, 1.4959, X10NiCrAlTi32-21, GX10NiCrSiNb32-20, X5NiCrAlTi31-20, X8NiCrAlTi32-21, X 12 CrNiTi 18 9 UNS N08800, N08810, N08811 Alloy 800, Alloy 800H, Alloy 800HT, Manaurite 900, Nicrofer 3220 H

GOEDKEURINGEN CE

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Mn	Si	Cr	Ni	Nb	Fe
0.1	4.6	0.28	21.2	33.2	1.2	Rem.

MECHANISCHE WAARDEN

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT		
As Welded	410	620	21	82		HRc

HERDROGEN Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD 21-33Mn

21-33MN 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663424273