


# CEWELD SP 80/20 NiAl

<b>TYPE</b>	Composite spray wire for bond coatings				
<b>TOEPASSINGEN</b>	SP 80/20 NiAl is widely used as a bond coat for subsequent thermal spray layers and as a one step build up material for dimensional restoration of aircraft engines.				
<b>EIGENSCHAPPEN</b>	SP 80/20 NiAl is a cored wire specifically designed for both, arc spraying and flame spraying. It is self bonding to most materials and requires minimal surface preparation. Bond strengths in excess of 9000 psi can be achieved on grit blasted surfaces. SP 80/20 NiAl exhibits good resistance to high temperature oxidation and abrasion, and excellent resistance to impact and bending. SP 80/20 NiAl can be machined and ground to a finish of 5 micro inches.				
<b>CLASSIFICATIE</b>	EN ISO	14919: 6.6			
<b>GESCHIKT VOOR</b>	Build up material for dimensional restoration of aircraft engines.				
<b>GOEDKEURINGEN</b>					
<b>LASPOSITIES</b>					
<b>TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)</b>	Si	Mn	Fe	Al	Ni
	0.4	0.2	0.1	20	Rem.
<b>MECHANISCHE WAARDEN</b>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Hardness
	As Welded				75 HB
<b>HERDROGEN</b>	Not required				
<b>GAS ACC. EN ISO 14175</b>	None				



# CEWELD SP 80/20 NiAl

SP 80/20 NIAL 3,15MM

Packaging	KG/unit	EanCode
K-415	5	8720663410030