



CEWELD FL 8111

TYPE Fluoride basic agglomerated flux for stainless steel SAW welding.

TOEPASSINGEN Sub arc flux suitable for a wide range of applications in offshore and general steelwork, cladding valves, shafts, tanks, steel mill rollers etc.

EIGENSCHAPPEN FL 8111 is a fluoride basic agglomerated flux for stainless steel SAW welding. Basicity: about 2,6 (according to Boniszewski) Current: DC or AC, in single or multi-wires. Grain size: 2-28

CLASSIFICATIE EN ISO 14174: SA FB 1 65 AC H5

GESCHIKT VOOR Submerged arc welding with stainless steel wires, AISI 410, 410NiMo, 308L, 316L, 2209 duplex, 347, 309L, 309LMo, 308H, super duplex, zeron 100, SAF 2507

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)

| CaO+MgO | SiO ₂ | Al ₂ O ₃ | CaF ₂ |
|---------|------------------|--------------------------------|------------------|
| 35 | 20 | 25 | 15 |

MECHANISCHE WAARDEN

HERDROGEN Not required

GAS ACC. EN ISO 14175



CEWELD FL 8111

FL 8111 0,2 - 2,8MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| Bag | 25 | 8720663404121 |