



# CEWELD SA 316L

**TYPE** Solid stainless steel welding wire for submerged arc welding

**TOEPASSINGEN** The alloy is widely used in the chemical and food-processing industries, as well as in shipbuilding, vessel and various types of architectural structure. Suitable for welding corrosion-resistant Cr-Ni-Mo steels with extremely low C-content at working temperatures up to 350°C.

**EIGENSCHAPPEN** SA 316L offers good general corrosion resistance, particularly to corrosion in acid and chlorinated environments. The alloy has a low carbon content which makes it particularly recommended when there is a risk of intergranular corrosion. can be used with our fused flux FL 880 or agglomerated fluxes FL 838 or FL 8111.

**CLASSIFICATIE**

AWS	A 5.9: ER316L
EN ISO	14343-A: S 19 12 3 L
W.Nr.	1.4430
F-nr	6
FM	5

**GESCHIKT VOOR** 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 4.4430  
 X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP)  
 316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN  
 UNS S31640, UNS S31603, UNS S31653, UNS S31600, UNS S31635

**GOEDKEURINGEN** CE

**LASPOSITIES**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**

C	Si	Mn	P	S	Cr	Ni	Mo
0.02	0.5	2	0.02	0.02	19	12	2.5

**MECHANISCHE WAARDEN**

Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness
				RT	-196°C	
As Welded	370	550	35	120	55	HRc

**HERDROGEN** Not required

**GAS ACC. EN ISO 14175**



# CEWELD SA 316L

SA 316L 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663414281

SA 316L 3,2MM

Packaging	KG/unit	EanCode
K-415	25	8720663414298