

CEWELD Powder 8812-Ni

TYPE	Carbide powder, agglomerated and sintered		
TOEPASSINGEN	carbide powder for wear resistant coatings produced by flame-, plasma or high velocity- flame-spraying (HVOF). Tungsten-Carbide-Nickel-coatings are resistant to abrasion and oxidation. In comparison with WC-Co layers they show an improved corrosion resistance in aqueous solutions. Plasma sprayed coatings can achieve a hardness of up to 1000 HV0.1 and tensile strength acc. to DIN 50160 of 60 N/mm ² . The maximum operating temperature is 750°C.		
EIGENSCHAPPEN	Crystal size of WC	Apparent Density (ISO 3923-2)	Particle Size Range in µm FSSS 4.3 – 5.4 g/cm ³ 22/5 - 38/15 - 53/22 Particle Shape Preponderant spherical
CLASSIFICATIE	EN ISO	14232-1	WC-Ni 88/12
GESCHIKT VOOR	Augers, impellers, shafts, hydraulics, pulling equipment, fan blades etc.		
GOEDKEURINGEN			
LASPOSITIONS			
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Ni		WC
	12		88
MECHANISCHE WAARDEN			
HERDROGEN	Not required		
GAS ACC. EN ISO 14175	None		