



# CEWELD AA 308LM

TYPE	Metal cored stainless steel welding wire.( Type 308L, 19 9L )						
TOEPASSINGEN	CEWELD® AA 308LM is suitable for welding stainless steels with an alloy content between 16 to 21% Cr and 8 to 13% Ni, stabilised or not. Boilers, tanks, agriculture, liquid storage tanks, food machinery, furniture.						
EIGENSCHAPPEN	CEWELD® AA 308LM has good general corrosion resistance. The alloy has a low carbon content, making it particularly recommended where there is a risk of intergranular corrosion. Enhanced productivity, improved weldability, better wetting properties compared to solid wires. Excellent weld metal quality and X-ray soundness.						
CLASSIFICATIE	AWS	A 5.22: EC308L					
	EN ISO	17633-A: T 19 9 L M M12 1					
	W.Nr.	1.4316					
	F-nr	6					
	FM	5					
GESCHIKT VOOR	<b>ISO 15608: 8.1 Austenitic ≤ 19 % Cr 9% Ni ,TÜV 1000: Gr. 21 - 22 (29 max.350°C),</b> 1.4301, 1.4306, 1.4307, 1.4308, 1.4311, 1.4312, 1.6900, 1.6901, 1.6902, 1.6903, 1.9606, 1.4541, 1.4546, 1.4550 X 5 CrNi 18 10, X 2 CrNi 19 11, X 5 CrNi 18 9, G-X 6 CrNi 18 9, X 12 CrNi 18 9, G-X 8 CrNi 18 10, X 6 CrNi 18 10, X 10 CrNiTi 18 10, X 5 CrNi 18 10 AISI 304, 304H, 312, 321H, 347, 347H, UNS S30409, S32109, S34709, S30400, S32100, S34700						
GOEDKEURINGEN	CE						
LASPOSITIES							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni
	0.02	0.55	1.4	0.015	0.008	21	11
MECHANISCHE WAARDEN	Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness
					-196°C		
	As Welded	430	600	40	35		HRC
HERDROGEN	Not required						
GAS ACC. EN ISO 14175	I1, M13, M12						